chanhvinh.com

Emerson & Cuming

ECCOBOND® 83 C
Silver Filled, Electrically Conductive Epoxy Adhesive

Key Feature:	Benefit:
• Silver filled	• Ultimate electrical and thermal conductivity
• Good bond strength	• Provides reliable and strong electrical connections
• Smooth, creamy paste	• Ease of use

Product Description:

ECCOBOND 83 C is a silver filled, electrically conductive epoxy adhesive resin. It is supplied as a smooth, creamy that is easier to mix, handle and apply than ECCOBOND 56 C. ECCOBOND 83 C bonds well to metals, glass, ceramics, and plastics and cures to yield excellent electrical and thermal conductivity.

Applications:

ECCOBOND 83 C was designed to make electrical connections where hot soldering is impractical or to make electrical connections to conductive plastics at locations which can not be subjected to high temperatures.

Instructions For Use:

Thoroughly read the information concerning health and safety contained in this bulletin before using. Observe all precautionary statements that appear on the product label and/or contained in individual Material Safety Data Sheets (MSDS).

To ensure the long term performance of the bonded assembly, complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt, and oils which can cause poor adhesion or corrosion in a bonded part. For information on proper substrate preparation, refer to the reprint “Good Adhesive Bonding Starts With Surface Preparation” available from Henkel Corporation.

Some separation of components is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use.

Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.

Blend components by hand, using a kneading motion, for 2-3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.

Apply the adhesive to all surfaces to be bonded and join together. In most applications only contact pressure is required.

Properties of Material As Supplied:

Property	Test Method	Unit	Value
Chemical Type			Epoxy
Appearance	Visual		Silver, thixotropic paste
Density	TP-13	g/cm^3	3.00

Choice of Curing Agents		
Curing agent	Catalyst 9	Catalyst B 97
Description	General purpose with good chemical resistance and physical strength.	High temperature resistant epoxy hardener with long working life. Good chemical resistance and good physical properties at elevated temperatures.
Type of cure	Room	Heat
Viscosity Pa.s cP	0.080 to 0.105 80 to 105	4 -8 4,000 - 8,000

Properties of Material As Mixed:

Property	Test Method	Unit	Value	
			Catalyst 9	Catalyst B 97
Mix Ratio-Amount of Catalyst per 100 parts of ECCOBOND 83 C		By Weight	3.5	1.0
Working Life (100 g @ 25°C)	ERF 13-70		45 minutes	24 hours
Density	TP-13	g/cm^3	2.81	2.95

chanhvinh.com

Cure Schedule:

Cure at any one of the recommended cure schedules. For optimum performance, follow the initial cure with a post cure of 2 - 4 hours at the highest expected use temperature.

Temperature	Cure Time	
°C	Catalyst 9	Catalyst B 97
65	60 minutes	
100	30 minutes	2 hours
125		30 minutes

Properties of Material After Application:

Property	Test Method	Unit	Value	
			Catalyst 9	Catalyst B 97
Tensile Lap Shear Strength aluminum to aluminum @ 25°C	TP-21	mPa psi	6.8 1,000	9.6 1,400
Coefficient of Thermal Expansion	TMA	10^{-6}/°C	45	45
Thermal Conductivity	ASTM-D-2214	W/m.K Btu-in/hr-ft^2-°F	2.6 18	2.6 18
Temperature Range of Use		°C	-40 to +130	-55 to +155
Outgassing[1] TML CVCM	NASA OUTGASSING	 % %	 0.64 0.02	
Volume Resistivity @ 25°C	TP-296	Ohm-cm	0.0004	0.0004

TPs are internal test procedures typically derived from ASTM or other norms. Copies of these test procedures can be obtained upon request.

[1] per NASA Reference Publication 1124. Sample tested was cured for 1 hour @ 66 °C.

Storage and Handling:

The shelf life of ECCOBOND 83 C is 6 months at 25°C. For best results, store in original, tightly covered containers. Storage in cool, clean and dry areas is recommended.

Health and Safety:

The ECCOBOND 83 C, like most epoxy compounds, possesses the ability to cause skin and eye irritation upon contact. Certain individuals may also develop an allergic reaction after exposure (skin contact, inhalation of vapors, etc.) which may manifest itself in a number of ways including skin rashes and an itching sensation. Handling this product at elevated temperatures may also generate vapors irritating to the respiratory system.

Good industrial hygiene and safety practices should be followed when handling this product. Proper eye protection and appropriate chemical resistant clothing should be worn to minimize direct contact. Consult the Material Safety Data Sheet (MSDS) for detailed recommendations on the use of engineering controls and personal protective equipment.

This information is only a brief summary of the available safety and health data. Thoroughly review the MSDS for more complete information before using this product.

Attention Specification Writers:

The values contained herein are considered typical properties only and are not intended to be used as specification limits.

Medical Implantable Disclaimer

"In the event this product is intended by you for use in implantation in the human body, you are hereby advised that Henkel Corporation has not performed clinical testing of these materials for implantation in the human body nor has Henkel Corporation sought, nor received, approval from the FDA for the use of these material in implantation in the human body. It is YOUR responsibility, as a manufacturer of any such device, to ensure that all materials and processes relating to the manufacture of any medical device fully comply with all applicable federal, state and local laws, rules, regulations and requirements as well as any such laws, rules, regulations, directives or other orders of any foreign country where such product is sold. If you have not undertaken the necessary investigations to ensure compliance you are advised NOT TO USE this product in the manufacture of any device which is to be implanted in the human body. No representative of ours has any authority to change the foregoing provisions."

© 2003

chanhvinh.com

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel and/or its affiliates in Germany and elsewhere.